



Product	Average Particle Size (% Retained)				Fiber Length	Viscosity (Water)	Viscosity (30W Oil)	Ash Content	Moisture Content	Oil Absorption	Common Uses
	20 Mesh	60 Mesh	100 Mesh	140 Mesh	Avg.	4% conc.	2% conc.	Max	Max	Times Weight	
CF100	35-72	6-17	1-3	2-4	1.31 mm	16,700 cP	140,000 cP	15%	7%	11X	Fireproof, Refractory, Textured Coatings
CF220	17-28	10-17	3-7	4-9	1.05 mm	8,400 cP	29,500 cP	27%	5%	9X	Gaskets, Mastics, Sound Dampening
CF315	10-18	13-21	4-8	4-10	1.05 mm	25,000 cP	35,500 cP	23%	5%	5X	Stone Mastic Asphalt (SMA)
CF325	9-17	12-19	4-8	5-10	0.83 mm	7,900 cP	35,700 cP	28%	5%	8X	Asphalt Roof & Pavement Coatings
CF335	8-17	11-18	4-8	4-10	0.87 mm	7,400 cP	38,300 cP	29%	5%	8X	Asphalt Roof & Pavement Coatings
CFS4060 5	0	10-30	8-14	9-23	0.53 mm	1,800 cP	7,400 cP	18%	5%	8X	Asphalt Roof & Pavement Coatings
CF425	0-1	7-18	6-13	8-19	0.72 mm	2,200 cP	8,200 cP	28%	5%	7X	Adhesives & Sealants, Asphalt Roof & Pavement Coatings
CF525	0	1-12	8-15	6-20	0.57 mm	2,400 cP	9,800 cP	25%	5%	6X	Adhesives & Sealants, Asphalt Roof & Pavement Coatings
CF725	0	0-8	8-14	13-26	0.54 mm	2,600 cP	6,700 cP	25%	5%	6X	Adhesives & Sealants, Asphalt Roof & Pavement Coatings
Drill Paper	<50	8-14	2-6	N/A	N/A	13,100 cP	110,300 cP	11%	10%	11X	Lost Circulation Systems, Drilling Fluids, Coatings